


# BARRA CROMADA

## Barra Normal

Grueso del cromo .0005", Dureza de la superficie: 68-72 Rc  
 Dureza de el centro: **20-28 Rc**, Material: C-1045  
 75,000 PSI yield

Número de Parte	Diámetro Exterior	Tolerancia	PSI Yield	Calidad del acero	Peso por metro
BC-0.500-75K	1/2"	0/-0.0015	75,000	1045	0.9 Kg
BC-0.625-75K	5/8"	0/-0.0015	75,000	1045	1.5 Kg
BC-0.750-75K	3/4"	0/-0.0015	75,000	1045	2.2 Kg
BC-0.875-75K	7/8"	0/-0.0015	75,000	1045	3.0 Kg
BC-1.000-75K	1"	0/-0.0015	75,000	1045	4.0 Kg
BC-1.125-75K	1 1/8"	0/-0.0015	75,000	1045	5.1 Kg
BC-1.250-75K	1 1/4"	0/-0.0015	75,000	1045	6.3 Kg
BC-1.375-75K	1 3/8"	0/-0.0015	75,000	1045	7.4 Kg
BC-1.500-75K	1 1/2"	0/-0.0015	75,000	1045	8.9 Kg
BC-1.750-75K	1 3/4"	0/-0.0015	75,000	1045	12.2 Kg
BC-2.000-75K	2"	0/-0.0015	75,000	1045	15.9 Kg
BC-2.250-75K	2 1/4"	0/-0.0015	75,000	1045	20.1 Kg
BC-2.500-75K	2 1/2"	0/-0.0015	75,000	1045	24.9 Kg
BC-2.750-75K	2 3/4"	0/-0.0015	75,000	1045	30.1 Kg
BC-3.000-75K	3"	0/-0.0015	75,000	1045	35.7 Kg
BC-3.500-75K	3 1/2"	0/-0.0015	75,000	1045	48.7 Kg
BC-4.000-75K	4"	0/-0.0015	75,000	1045	63.6 Kg
BC-4.500-75K	4 1/2"	0/-0.0015	75,000	1045	80.6 Kg
BC-5.000-75K	5"	0/-0.0015	75,000	1045	99.5 Kg
BC-5.500-75K	5 1/2"	0/-0.0015	75,000	1045	116.2 Kg
BC-6.000-75K	6"	0/-0.0015	75,000	1045	143.1 Kg



## Barra Endurecida

Grueso del cromo .0005", Dureza de la superficie: 68-72 Rc  
 Dureza de el centro: **50-52 Rc**, Material: C-1050  
 100,000 PSI yield

Número de Parte	Diámetro Exterior	Tolerancia	PSI Yield	Calidad del acero	Peso por metro
BC-1.500-100K	1 1/2"	0/-0.0015	100,000	1050	8.9 Kg
BC-1.750-100K	1 3/4"	0/-0.0015	100,000	1050	12.2 Kg
BC-2.000-100K	2"	0/-0.0015	100,000	1050	15.9 Kg
BC-2.500-100K	2 1/2"	0/-0.0015	100,000	1050	24.9 Kg
BC-2.750-100K	2 3/4"	0/-0.0015	100,000	1050	30.1 Kg
BC-3.000-100K	3"	0/-0.0015	100,000	1050	35.7 Kg
BC-3.500-100K	3 1/2"	0/-0.0015	100,000	1050	48.7 Kg

